RULE 236 WOOD PRODUCTS COATING OPERATIONS

Adopted 11-03-94 (Amended 2-09-95, 4-10-97, 8-14-97, 10-14-10 [Effective 7-1-11])

CONTENTS

100 GENERAL

- 101 PURPOSE
- 102 APPLICABILITY
- 103 SEVERABILITY
- 104 EXEMPTIONS

200 DEFINITIONS

- 201 AEROSOL-SPRAY COATING
- 202 AFFECTED POLLUTANT
- 203 AIR ASSISTED AIRLESS SPRAY
- 204 BINDERS
- 205 CAPTURE EFFICIENCY
- 206 CLEANUP MATERIAL
- 207 CLEAR TOPCOAT
- 208 CLOSED CONTAINER
- 209 COATING
- 210 CONTROL DEVICE EFFICIENCY
- 211 CONVERSION VARNISH
- 212 CRACKLE LACQUER
- 213 DETAILING OR TOUCH-UP GUNS
- 214 DIP COAT
- 215 ELECTROSTATIC APPLICATION
- 216 EMISSIONS UNIT
- 217 EMISSION CONTROL SYSTEM
- 218 ENCLOSED GUN CLEANER
- 219 EXEMPT COMPOUNDS
- 220 FAUX FINISH
- 221 FILLER
- 222 FLOW COATING
- 223 HIGH-SOLIDS
- 224 HIGH-VOLUME-LOW-PRESSURE (HVLP) SPRAY
- 225 IMITATION WOOD GRAIN
- 226 INKS
- 227 LEAF FINISH
- 228 LOW-SOLIDS COATING
- 229 LOW-VOLUME, LOW-PRESSURE (LVLP) EQUIPMENT
- 230 MOLD-SEAL COATING
- 231 MULTI-COLORED COATING
- 232 NEW WOOD PRODUCT
- 233 NON-SHOP ARCHITECTURAL COATING OPERATIONS
- 234 OPAQUE STAINS
- 235 PIGMENTED COATINGS
- 236 REACTIVE DILUENT
- 237 REFINISHING OPERATION
- 238 REPAIR
- 239 ROLL COATER
- 240 SEALER
- 241 SEMITRANSPARENT STAIN

- 242 SIMULATED WOOD MATERIALS
- 243 STAIN
- 244 STENCIL COATING
- 245 STRIPPER
- 246 SURFACE PREPARATION MATERIAL
- 247 TINT
- 248 TONER
- 249 TOUCH-UP
- 250 VOC COMPOSITE PARTIAL VAPOR PRESSURE
- 251 VOLATILE ORGANIC COMPOUND (VOC)
- 252 VOC CONTENT
- 253 WASH COAT
- 254 WOOD PANEL
- 255 WOOD PRODUCTS
- 256 WOOD PRODUCT COATING APPLICATION OPERATIONS

300 STANDARDS

- 301 APPLICATION EQUIPMENT REQUIREMENTS
- 302 LIMITS FOR VOC CONTENT OF COATINGS FOR NEW WOOD PRODUCTS
- 303 LIMITS FOR VOC CONTENT OF COATINGS FOR REFINISHING, REPAIRING, PRESERVING, OR RESTORING WOOD PRODUCTS
- 304 LIMITS OF VOC CONTENT FOR STRIPPERS
- 305 EMISSION CONTROL SYSTEM
- 306 REQUIREMENTS FOR SURFACE PREPARATION AND CLEANUP MATERIALS

400 ADMINISTRATIVE REQUIREMENTS

- 401 PROHIBITION OF SPECIFICATION
- 402 PROHIBITION OF POSSESSION
- 403 PROHIBITION OF SALE OR MANUFACTURE
- 404 LABELING REQUIREMENTS, VOC CONTENT
- 405 OPERATION AND MAINTENANCE PLAN

500 MONITORING AND RECORDS

- 501 RECORDKEEPING
- 502 RETENTION OF RECORDS
- 503 TEST METHODS

100 GENERAL

101 PURPOSE: To establish limits on the emission of volatile organic compounds (VOC) from coatings and strippers used on wood products, and from products used in surface preparation and cleanup.

102 APPLICABILITY:

- 102.1 <u>Business Category:</u> The provisions of this rule shall apply to any person who uses, manufactures, blends, sells, repackages, distributes, or specifies wood products coatings and/or strippers to be used for the coating and/or surface preparation of wood products, including furniture, cabinets, and custom replica furniture.
- **SEVERABILITY:** If any section, subsection, sentence, clause, phrase, or portion of this rule is, for any reason, held invalid, unconstitutional or unenforceable by any court of competent jurisdiction, that portion shall be deemed as a separate, distinct, and independent provision, and the holding shall not affect the validity to the remaining portions of the rule.

104 EXEMPTIONS:

- 104.1 <u>Exemption, Residential:</u> Residential non-commercial operations are exempt from all provisions of this rule.
- 104.2 <u>Exemption, Non-Shop Architectural Coating Operations:</u> The coating of stationary structures and their appurtenances in a non-shop environment, is subject to Rule 218, ARCHITECTURAL COATINGS, and is exempt from all provisions of this rule.
- 104.3 <u>Exemption, Aerosol Spray Coatings:</u> Aerosol wood products coatings sold in non-refillable aerosol containers are exempt from all provisions of this rule.
- 104.4 Exemption, Panels and Siding: The factory application of wood products coatings in the manufacturing of finished wood panels intended for attachment to the inside walls of buildings, including, but not limited to, homes and office buildings, mobile homes, trailers, prefabricated buildings and similar structures, is subject to Rule 238, FACTORY COATING OF FLAT WOOD PANELING, and is exempt from all provisions of this rule.
- 104.5 <u>Exemption, Other:</u> The application of coatings by template or stencil to add designs, letters or numbers to wood products, and the application of coatings to wooden musical instruments are exempt from all provisions of this rule.
- 104.6 <u>Partial Exemption, Low Volume:</u> Businesses using less than 55 gallons per year of wood products coatings and/or strippers (singly or in any combination) are exempt from all provisions of this rule with the exception of Section 501, Recordkeeping.
- 104.7 <u>Partial Exemption, Specific Finishes:</u> Coatings used to produce the following finishes are exempt from the provisions of Sections 302, 303 and 304, provided that records are maintained as specified in Section 501, Recordkeeping:
 - 104.7.1 Crackle lacquers;
 - 104.7.2 Faux finishes;
 - 104.7.3 Imitation wood grain;
 - 104.7.4 Leaf finishes.

- 104.8 Exemption, <u>Tints</u>: Tints applied to stains in quantities not to exceed one pint of tint in any operating day are exempt from all provisions of this rule, except for records. Records shall be maintained and reported as specified in Sections 501.1.4 and 501.2.2
- 104.9 <u>Exemption From Requirements of Other District Rules:</u> Any wood products coating, stripper or cleaning solvent subject to the VOC limitations of this rule, Sections 302, 303, and 304, is exempt from the requirements of Rule 219, ORGANIC SOLVENTS.

200 DEFINITIONS

- **201 AEROSOL-SPRAY COATING:** A coating which is sold in a hand-held, pressurized, non-refillable container of 1 liter (1.1 quarts) or less, and which is expelled from the container in a finely divided spray when a valve on the container is depressed.
- 202 AFFECTED POLLUTANT: Volatile organic compounds (VOC), as defined in Section 251.
- **203 AIR ASSISTED AIRLESS SPRAY:** Equipment used to apply coatings that uses fluid pressure to atomize coating and air pressure between 0.1 and 20 psig to adjust the spray pattern.
- **204 BINDERS:** Non-volatile polymeric organic materials (resins) which form surface film in coating applications.
- **205 CAPTURE EFFICIENCY:** Expressed in percent, capture efficiency is the ratio of the weight of the VOC in the effluent stream entering a control device to the weight of the VOC emitted from wood product coating operations, both measured simultaneously in accordance with Section 503.4, and calculated by the following equation:

Capture Efficiency =
$$\begin{array}{c} W_c \\ ----- \\ W_e \end{array}$$
 X 100

Where: W_c = Weight of VOC entering the control device

W_e = Weight of VOC discharged from the coating operations

- **206 CLEANUP MATERIAL:** A VOC-containing material used to clean application equipment used in wood products coating operations.
- **207 CLEAR TOPCOAT:** The final coating which contains binders, but not opaque pigments, and is specifically formulated to form a transparent or translucent solid protective film.
- **208 CLOSED CONTAINER:** A container which has a cover where the cover meets with the main body of the container without any gaps between the cover and the main body of the container.
- **209 COATING:** A material which is applied to a surface and which forms a film in order to beautify and/or protect such surface. "Coating" includes, but is not limited to, materials such as topcoats, stains, sealers, fillers, conversion varnish, pigmented coating, multicolored coating, moldseal coating, washcoat, and toner.

210 CONTROL DEVICE EFFICIENCY: Expressed in percent, control device efficiency is the ratio of the weight of the VOC removed by the control device from the effluent stream entering the control device to the weight of VOC in the effluent stream entering the control device, both measured simultaneously in accordance with Section 503.5, and calculated by the following equation:

Control Device Efficiency =
$$(W_c - W_a)$$

 W_c X 100

Where: W_c = Weight of VOC entering the control device

W_a = Weight of VOC discharged from the control device

- 211 CONVERSION VARNISH: A coating comprised of a homogeneous (alkyd-amino resin) liquid which, when acid catalyzed and applied, hardens upon exposure to air or heat, by evaporation and polymerization, to form a continuous film that imparts protective or decorative properties to wood surfaces. When used as a self sealing system or as a pigmented coating, conversion varnish shall not be subject to the July 1, 2005 VOC limit for Sealers or for Pigmented Coatings, as specified in Section 302.
- **212 CRACKLE LACQUER:** A clear or pigmented topcoat intended to produce a cracked or crazed appearance when dry.
- **213 DETAILING OR TOUCH-UP GUNS:** Small air spray equipment, including air brushes, that operates at no greater than five (5) cfm air flow and no greater than 50 psig air pressure and is used to repair or touch-up portions of wood products.
- **214 DIP COAT:** A coating which is applied by dipping an object into a vat of coating material and allowing any excess coating material to drain off.
- **215 ELECTROSTATIC APPLICATION:** The electrical charging of atomized coating droplets for deposition by electrostatic attraction.
- **216 EMISSIONS UNIT:** An identifiable operation or piece of process equipment such as an article, machine, or other contrivance which controls, emits, may emit, or results in the emissions of any affected pollutant directly or as fugitive emissions.
- 217 EMISSION CONTROL SYSTEM: A system for reducing emissions of VOC from coating operations. It consists of (1) equipment which captures drying oven exhaust and fugitive emissions from the line and transports them to the control device, and (2) a VOC control device which destroys the VOC or otherwise limits the emission of VOC to the atmosphere. The capture efficiency and the control device efficiency are calculated in accordance with Sections 205 and 210, respectively.

The Emission Control System Efficiency is calculated by the following equation:

Efficiency = Capture Efficiency X Control Device Efficiency / 100

218 ENCLOSED GUN CLEANER:

218.1 A device that is used for the cleaning of spray guns, pots and hoses, that has an enclosed solvent container, is not open to the ambient air when in use, and has a mechanism to force the cleanup material through the gun while the cleaner is in operation; or

- 218.2 A device that is used for the cleaning of spray guns, pots and hoses, that has an enclosed solvent container, uses non-atomized solvent flow to flush the spray equipment and collects and returns the discharged solvent to the enclosed container.
- **219 EXEMPT COMPOUNDS:** For the purposes of this rule, exempt compounds are as described in Rule 102, DEFINITIONS.
- **220 FAUX FINISH:** A finish intended to simulate a surface other than wood, including stone, sand, slate, marble, metal, metal flake or leather.
- 221 FILLER: A preparation used to fill in cracks, grains, etc., of wood before applying a coating.
- **FLOW COATING:** A coating application system where paint flows over the part and the excess coating drains back into the collection system.
- **HIGH-SOLIDS:** A coating containing more than one (1) pound of solids per gallon of coating, by weight, when measured in accordance with Section 503.1, and which can include wiping stains, glazes, and opaque stains.
- **224 HIGH-VOLUME-LOW-PRESSURE (HVLP) SPRAY:** Equipment used to apply coatings by means of a spray gun which is designed to be operated and which is operated between 0.1 and 10 psig air pressure measured dynamically at the center of the air cap and at the air horns.
- **225 IMITATION WOOD GRAIN:** A hand applied finish that simulates the appearance of a specific natural wood grain.
- **226 INKS:** A fluid that contains dyes and/or colorants and is used to make markings but not to protect surfaces.
- **227 LEAF FINISH:** A finish used in conjunction with metal leaf or foil.
- **228 LOW-SOLIDS COATING:** A coating containing one (1) pound of solids per gallon of coating or less, by weight, when measured in accordance with Section 503.1, and which can include semi-transparent stains, toners, and washcoats.
- **229 LOW-VOLUME, LOW-PRESSURE (LVLP) EQUIPMENT:** Spray coating application equipment with air pressure between 0.1 and 10.0 psig and air volume less than 15.5 cfm per spray gun and which operates at a maximum fluid delivery pressure of 50 psig.
- **230 MOLD-SEAL COATING:** The initial coating applied to a new mold or repaired mold to provide a smooth surface which, when coated with a mold release coating, prevents products from sticking to the mold.
- **MULTI-COLORED COATING:** A coating which exhibits more than one (1) color when applied and which is packaged in a single container and applied in a single coat.
- **232 NEW WOOD PRODUCT:** A wood product which has not been previously coated or a wood product from which uncured coatings have been removed to repair flaws in initial coatings applications.
- 233 NON-SHOP ARCHITECTURAL COATING OPERATIONS: The commercial application of coatings to stationary structures and/or their appurtenances, to mobile homes, to pavements, or to curbs, and not conducted inside, or on the premises of, a factory or shop building facility.

- **234 OPAQUE STAINS:** Stains not classified as semitransparent stains, which contain pigments which give character to wood.
- **235 PIGMENTED COATINGS:** Opaque coatings which contain binders and colored pigments which are formulated to hide the wood surface, either as an undercoat or topcoat.
- **236 REACTIVE DILUENT:** A liquid component of a coating which is a VOC during application, and one in which, through chemical or physical reactions, such as polymerization, becomes an integral part of a finished coating.
- **237 REFINISHING OPERATION:** The steps necessary to remove cured coatings and to repair, preserve, or restore a wood product.
- **238 REPAIR:** Recoating portions of previously coated product to cover mechanical damage to the coating following normal painting operations.
- **239 ROLL COATER:** A series of mechanical rollers that forms a thin coating film on the surface of roller, which is applied to a substrate by moving the substrate underneath the roller.
- **240 SEALER:** A coating containing binders, which seals the wood prior to application of the subsequent coatings.
- **241 SEMITRANSPARENT STAIN:** A stain containing dyes and/or semi-transparent pigments which are formulated to enhance wood grain and change surface color but not to conceal surface grain, and include sap stain and non-grain raising stains. Semitransparent stains with greater than one (1) pound of solids per gallon of coating shall be considered opaque stains.
- **242 SIMULATED WOOD MATERIALS:** Materials, such as plastic, glass, metal, etc., that are made to give a wood-like appearance or are processed like a wood product.
- **STAIN:** A semitransparent or opaque coating labeled and formulated to change the color of a surface, but not conceal the grain pattern or texture.
- **244 STENCIL COATING:** An ink or a pigmented coating which is rolled or brushed onto a template or stamp in order to add identifying letters and/or numbers to wood products.
- 245 STRIPPER: A liquid used to remove cured coatings, cured inks, and/or cured adhesives.
- **246 SURFACE PREPARATION MATERIAL:** A VOC-containing material applied to the surface of any wood product, prior to the application of coatings, to clean the wood product or to promote the adhesion of subsequent coatings.
- **247 TINT:** A colorant added in small quantities to a stain to achieve a particular color for a finished product.
- **248 TONER:** A wash coat which contains binders and dyes or pigments to add tint to a coated surface.
- **249 TOUCH-UP:** A coating used to cover minor coating imperfections appearing after the main coating operation.

250 VOC COMPOSITE PARTIAL VAPOR PRESSURE: VOC composite partial vapor pressure for determination of compliance with Section 304 shall be calculated by the following equation:

$$PP_{c} = \frac{\sum_{i=1}^{n} (W_{i})(VP_{i})/MW_{i}}{\frac{W_{w}}{MW_{w}} + \frac{W_{e}}{MW_{e}} + \sum_{i=1}^{n} WSUB \frac{i}{MW_{i}}}$$

 $PP_{c} = W_{i} = W_{w} = W_{e} = MW_{i} = MW_{w} = MW_{$ VOC composite partial pressure at 20°C, in mm Hg Where:

Weight of the "I"_{th} VOC compound, in grams

Weight of water, in grams

Weight of exempt compounds, in grams

Molecular weight of the "I"_{th} VOC compound, in (g/g-mole)

Molecular weight of water, in (g/g-mole)

 $MW_e =$ Molecular weight of exempt compound, in (g/g-mole)

Vapor pressure of the "I"_{th} VOC compound at 20°C, in mmHg

251 VOLATILE ORGANIC COMPOUND (VOC): Any chemical compound containing at least one atom of carbon, except for the Exempt Compounds listed in Rule 102, DEFINITIONS.

252 VOC CONTENT:

Regulatory VOC Content: The weight of VOC per combined volume of VOC and coating solids, shall be calculated by the following equation:

$$G_{I} = \frac{W_{v} - W_{w} - W_{ec}}{V_{m} - V_{w} - V_{ec}}$$

Where: $G_1 =$ Weight of VOC per liter of coating, less water and less

exempt compounds

exempt compounds $W_v = Weight of all volatile compounds, in grams$ $W_w = Weight of water, in grams$ $W_{ec} = Weight of exempt compounds, in grams$ $V_m = Volume of coating material, in liters$ $V_w = Volume of water, in liters$

Volume of exempt compounds, in liters

Actual VOC Content: The weight (in grams) of VOC per liter of wood products coating material is expressed as grams VOC per liter of material, and shall be calculated using the following:

$$G_A = \frac{(W_v - W_w - W_{ec})}{v_m}$$

Where: G_A Weight of VOC per liter of total coating

Weight of all volatile compounds, in grams

Weight of water, in grams

Weight of exempt compounds, in grams

Volume of material, including any added VOC-containing solvents or reducers but excluding any colorants added to tint

the base, in liters

- **253 WASH COAT:** A coating, containing binders, which penetrates into and seals wood, prevents undesired staining, and seals in wood pitch. Washcoats with greater than one (1) pound of solids per gallon of coating shall be considered sealers.
- **WOOD PANEL:** Any piece of wood, or wood composition, which is solid or laminated, and which is larger than 10 square feet in size, and which is not subsequently cut into smaller pieces.
- **WOOD PRODUCTS:** Surface-coated objects such as cabinets (kitchen, bath and vanity), tables, chairs, beds, sofas, shutters, doors, trim, containers, tools, ladders, art objects, and any other objects made of solid wood and/or wood composition and/or of simulated wood material used in combination with solid wood or wood composition.
- **256 WOOD PRODUCT COATING APPLICATION OPERATIONS:** A combination of coating application steps which may include use of spray guns, flash-off areas, spray booths, ovens, conveyors, and/or other equipment operated for the purpose of applying coating to wood products.

300 STANDARDS

- **301 APPLICATION EQUIPMENT REQUIREMENTS:** A person subject to the provisions of this rule shall not apply any wood product coating to any wood products, unless one of the following application methods is used:
 - 301.1 Hand application methods, such as brush or roller;
 - 301.2 Roll coater;
 - 301.3 Dip coat;
 - 301.4 Flowcoat;
 - 301.5 High Volume Low Pressure spray equipment;
 - 301.6 Low Volume Low Pressure spray equipment;
 - 301.7 Air assisted airless, for touch-up and repair only;
 - 301.8 Electrostatic application equipment;
 - 301.9 Any other equivalent method which has been approved in writing by the Air Pollution Control Officer.
- 302 LIMITS FOR VOC CONTENT OF COATINGS FOR NEW WOOD PRODUCTS: Except as provided in Sections 103 and 305, no person shall apply any coatings to a new wood product, or use VOC-containing solvents, if such materials have a VOC content exceeding the applicable limits specified in the following table. The VOC content of coatings, except low-solid stains, toners, washcoats and solvents, shall be determined in accordance with Sections 252.1 (VOC regulatory content) and 503.1. The VOC content of low-solid stains, toners washcoats and solvents, shall be determined in accordance with Sections 252.2 (VOC actual content) and 503.1. VOC limits expressed in grams VOC per liter of coating shall be used.

LIMITS FOR VOC CONTENT OF COATINGS FOR NEW WOOD PRODUCTS

SPECIFIC MATERIAL	VOC LIMITS VOC Regulatory Content, Grams VOC Per Liter of Coating Less Water and Exempt Compounds, as defined in Section 252.1 (lb/gal)
Clear Topcoats	275 (2.3)
Conversion Varnish	550* (4.6)
Filler	275 (2.3)
High-Solid Stain	350 (2.9)
Inks	500 (4.2)
Mold-Seal Coating	750 (6.2)
Multi-colored Coating	275 (2.3)
Pigmented Coating	275* (2.3)
Sealer	275* (2.3)
	VOC LIMITS VOC Actual Content, Grams VOC per Liter of Material, as defined in Section 252.2 (lb/gal)
Low Solid Stains, Toners and Washcoats	120 (1.0)
	VOC LIMITS VOC Actual Content, Grams VOC Per Liter of Material, as defined in Section 252.2 (lb/gal)
Surface Prep and Clean-up Solvents Containing VOC's	25 (0.2)

^{* (}See Section 211 for special conditions for Conversion Varnish)

- 302.1 Notwithstanding the VOC limits specified in this section, a person may apply a sealer with a VOC content not exceeding 680 grams/liter, provided that the topcoat used on the same wood product does not exceed 275 grams/liter.
- 303 LIMITS FOR VOC CONTENT OF COATINGS FOR REFINISHING, REPAIRING, PRESERVING, OR RESTORING WOOD PRODUCTS: Except as provided in Sections 103 and 305, no person shall apply any coatings to refinish, repair, preserve, or restore a wood product, or use VOC-containing solvents, if such materials have a VOC content exceeding the applicable limits specified in the following table. The VOC content of coatings, except low-solid stains, toners, and washcoats, shall be determined in accordance with Sections 252.1 and 503.1. The VOC content of low-solid stains, toners and washcoats and VOC-containing solvents shall be determined in accordance with Sections 252.2 and 503.1. VOC limits expressed in grams per liter shall be used.

LIMITS FOR VOC CONTENT OF COATINGS TO REFINISH, REPAIR, PRESERVE OR RESTORE

SPECIFIC MATERIAL	VOC LIMITS VOC Regulatory Content, Grams VOC Per Liter of Coating Less Water and Exempt Compounds, as defined in Section 252.1 (lb/gal)
Clear Topcoats	680 (5.7)
Conversion Varnish	550* (4.6)
Filler	500 (4.2)
High-Solid Stain	700 (5.9)
Inks	500 (4.2)
Mold-Seal Coating	750 (6.3)
Multi-colored Coating	680 (5.7)
Pigmented Coating	600* (5.0)
Sealer	680* (5.7)
	VOC LIMIT VOC Actual Content, Grams VOC Per Liter of Material, as defined in Section 252.2 (lb/gal)
Low Solid Stains, Toners and Washcoats	480 (4.0)
	VOC LIMIT VOC Actual Content, Grams VOC Per Liter of Material, as defined in Section 252.2 (lb/gal)
Surface Prep or Clean-up Solvents Containing VOC's	25 (0.2)

^{* (}See Section 211 for special conditions for Conversion Varnish)

- **304 LIMITS OF VOC CONTENT FOR STRIPPERS:** A person shall not use a stripper on wood products unless:
 - 304.1 The stripper contains less than 350 grams of VOC per liter of material; or
 - 304.2 The VOC composite partial vapor pressure for the stripper is 2 mm Hg (0.04 psia) or less at 20°C (68°F), as calculated pursuant to Section 250.

305 EMISSION CONTROL SYSTEM:

305.1 As an alternative, a person may comply with the VOC limits specified in Sections 302, 303, and 304, by using an approved air pollution control system consisting of a capture system and a control device, which reduces VOC emissions from the application of wood products coatings or strippers by an equivalent or greater amount than the limits specified in Sections 302, 303, and 304, with the written approval of

the Air Pollution Control Officer. In order to achieve an equivalent or greater level of VOC reduction, the minimum allowable emission control system efficiency of such a system, when calculated pursuant to Section 217, shall be the efficiency calculated by the following equation:

$$C.E. = 1 - \left(\frac{(VOC_{LWc})}{(VOC_{LWn,Max})}X\frac{(1 - (VOC_{LWn,Max}/(D_{n,Max}))X100}{(1 - (VOC_{LWc}/D_c))}X100\right)$$

Where: C.E. Minimum allowable emission control system efficiency, percent VOC_{LWc} VOC Limit of Rule 236, less water and less exempt compounds, pursuant to Sections 302, 303, and/or 304 Maximum VOC content of non-compliant coating $VOC_{LWn,Max}$ used in conjunction with a control device, less water and less exempt compounds Density of solvent, reducer, or thinner contained $D_{n.Max}$ in the non-compliant coating, containing the maximum VOC content of the multi-component coating, g/L D_c Density of corresponding solvent, reducer, or thinner used in the compliant coating system (= 880 g/L)

- 305.2 The capture system shall vent all drying oven exhaust to the control device and shall have one or more inlets for collection of fugitive emissions; and
- 305.3 During any period of operation of a thermal incinerator, combustion temperature shall be continuously monitored; and
- 305.4 During any period of operation of a catalytic incinerator, exhaust gas temperature shall be continuously monitored; and
- 305.5 Written approval for the use of such equipment is obtained from the Air Pollution Control Officer prior to installation or use of the equipment.
- **306 REQUIREMENTS FOR SURFACE PREPARATION AND CLEANUP MATERIALS:** Any person subject to this rule shall comply with the following requirements:
 - 306.1 Spray gun nozzles only, may be soaked in solvent-based materials for cleaning, provided the container (not to exceed five (5) gallons in size) is kept tightly covered at all times except when accessing the container.
 - 306.2 Closed, non leaking, and non-absorbent containers shall be used for the disposal of cloth or paper used for surface preparation, cleanup, and coating removal.
 - 306.3 VOC-containing materials shall be stored in containers, which are closed when not in use, and shall be disposed of in a manner that the VOC's are not emitted into the atmosphere.
 - 306.4 A person shall not use solvent-based VOC-containing materials for the cleanup of spray equipment used in wood products coating application operations, unless the spray equipment is disassembled and cleaned in an enclosed gun cleaner.

306.5 A person shall not perform surface preparation or cleanup with a material containing VOC's in excess of 25 grams per liter in accordance with VOC limit standards in Sections 302 and 303.

400 ADMINISTRATIVE REQUIREMENTS

- **401 PROHIBITION OF SPECIFICATION:** No person shall require for use or specify the application of any coating subject to the provisions of this rule that does not meet the limits and requirements of this rule. The prohibition of this Section shall apply to all written or oral contracts under the terms of which any coating is to be applied to any wood product at any physical location within the District.
- **402 PROHIBITION OF POSSESSION:** No person shall possess any coating subject to the provisions of this rule that does not meet the limits and requirements of the rule.

403 PROHIBITION OF SALE OR MANUFACTURE:

- 403.1 No person shall manufacture, blend, repackage for sale, supply, sell, offer for sale, or distribute within the District, any coating with a VOC content in excess of the limits specified in Section 302 or 303 or 304. This shall apply to the sale of any non-compliant coating which will be applied at any physical location within the jurisdiction of the District.
- 403.2 The provision of Section 403.1 shall not apply to the application of coatings where either: (a) The product is used exclusively within a emission control systems as allowed in Section 305; or (b) For coatings for use outside of the District.
- 404 LABELING REQUIREMENTS, VOC CONTENT: Each container of any coating, surface preparation material, or cleanup material, or stripper manufactured shall display its maximum VOC content of the coating, as applied, and after any thinning as recommended by the manufacturer, or shall have this information provided in a product data sheet supplied with the container. VOC content shall be displayed as grams of VOC per liter of coating (less water and less exempt solvent, and excluding any colorant added to tint bases), surface preparation and cleanup material, or stripper. VOC content displayed may be calculated using product formulation data, or may be determined using the test method in Section 503.1. Alternatively, containers for strippers subject to the provisions of Section 304 may display only the partial vapor pressure.
- 405 OPERATION AND MAINTENANCE PLAN: A person using an emission control system pursuant to Section 305, as a means of alternate compliance with this rule, as provided in Sections 302, 303 and 304, must submit an Operation and Maintenance Plan for the emission control system to the Air Pollution Control Officer for approval. A person proposing to install a new emission control system as a means of alternate compliance with this rule shall submit in addition to an Operation and Maintenance Plan, an application for Authority to Construct, pursuant to Rule 501, GENERAL PERMIT REQUIREMENTS. The Plan shall specify operating and maintenance procedures which will demonstrate continuous operation of the emission control system during periods of emissions-producing operations. The Plan shall also specify which records must be kept to document these operating and maintenance procedures. These records shall comply with the requirements of Sections 501 and 502. The Plan shall be implemented upon approval of the Air Pollution Control Officer.

500 MONITORING AND RECORDS

501 RECORDKEEPING: In addition to any applicable record keeping requirements of either Rule 502, NEW SOURCE REVIEW, Rule 507, FEDERAL OPERATING PERMIT PROGRAM, and Rule 511, POTENTIAL TO EMIT, or any other District rule which may be applicable, any

person subject to this rule shall maintain the following records in order to evaluate compliance:

501.1 Product Data:

- A data sheet, material list, or invoice giving material name, manufacturer identification, material application, and VOC content.
- 501.1.2 Any catalysts, reducers, or other components used, and the mix ratio.
- 501.1.3 The applicable VOC limit from Section 302 or 303 and the actual VOC content of the wood product coating as applied.
- Name, description, container size and actual VOC content of any tints used to color stains for coating wood products.

501.2 Product Usage and Frequency:

- For persons using coatings or materials which comply with the VOC limits specified in Sections 302, 303, and 304, records shall be maintained on a monthly basis, showing the type and volume of coatings, strippers and surface preparation and cleanup materials used. Coating type shall be designated according to the coating categories as listed in Sections 302, 303, and 304.
- Persons using stains and/or tints and subject to this rule shall maintain records on a monthly basis that provide the following information as applicable:

Name, description, container size, and actual VOC content of any tints used to color stains.

Usage of any tint is limited to one pint of tint in any operating day. Records of any tint use shall be maintained on a monthly basis and submitted to the District when requested.

- 501.2.3 If at any time a person uses coatings or materials exceeding the VOC limits specified in Sections 302, 303, and 304, records shall be maintained on a daily basis showing the type and volume of materials used
- For persons using tints to color stains, usage is limited to one pint or less in any operating day. Records of any tint use shall be maintained on a daily basis and submitted monthly to the Placer Air Pollution Control District.

501.3 Emission Control System:

- A person using an emission control system as a means of alternate compliance pursuant to Section 305, shall maintain records on a monthly basis, showing the type and volume of coatings and solvents used.
- A person using an emission control system as a means of alternate compliance with this rule pursuant to Section 305, shall maintain daily records of key system operating and maintenance procedures which will demonstrate continuous operation and compliance of the emission control system during periods of emission-producing activities. Key

system operating parameters are those necessary to ensure compliance with the requirements of Section 305.

502 RETENTION OF RECORDS: All records required by this rule shall be retained for at least three years, except for sources subject to Rule 507, FEDERAL OPERATING PERMIT PROGRAM, which shall be retained for at least five years. Such records shall be made available to the Air Pollution Control Officer upon request.

503 TEST METHODS

- 503.1 <u>Determination of VOC Content:</u> VOC content, solids content, and water content of wood product coatings, strippers, and surface preparation and cleanup materials, subject to this rule, shall be determined in accordance with United States Environmental Protection Agency (U.S. EPA) Method 24 and Sections 252, 253 or 254 of this rule, as applicable.
- 503.2 <u>Determination of Composition of VOC:</u> The composition of VOC shall be as specified on the manufacturer's label or data sheet, or as determined by ASTM Method E260-96, "Standard Practice for Packed Column Gas Chromatograph".
- Determination of Compounds Exempt From VOC Definition: Exempt Compounds per Section 219 of this rule, and as defined in Rule 102, DEFINITIONS, shall be determined in accordance with ASTM D4457-85, "Standard Test Method for Determination of Dichloromethane and 1,1,1-Trichloroethane in Paints and Coatings by Direct Injection into a Gas Chromatograph", or ARB Method 432. If any of the perfluorocarbons or volatile cyclic and linear methyl siloxanes are being claimed as exempt compounds, the person making the claim must state in advance which compounds are present, and the U.S. EPA-approved test method used to make the determination of these compounds.
- 503.4 <u>Determination of Capture Efficiency:</u> Efficiency of the capture system shall be determined in accordance with U.S. EPA "Guidelines for Determining Capture Efficiency, January 9, 1995". Individual capture efficiency test runs subject to the U.S. EPA technical guidelines, calculated in accordance with Section 205, shall be determined by:
 - 503.4.1 40 CFR 51, Appendix M, Methods 204-204F; or
 - The South Coast Air Quality Management District "Protocol for Determination of Volatile Organic Compound (VOC) Capture Efficiency"; or
 - 503.4.3 Any other method approved by the U.S. EPA, the California Air Resources Board, and the Air Pollution Control Officer.
- 503.5 <u>Determination of Control Device Efficiency:</u> Efficiency of the emission control device shall be based upon test measurements made in accordance with (1) U.S. EPA Method 25 or 25A, for VOC concentration, and (2) U.S. EPA Method 2 or 2C for flow rates, as applicable, and calculated in accordance with Section 210. U.S. EPA Method 18 or CARB Method 422 "Determination of Volatile Organic Compounds in Emissions from Stationary Sources" may be used to determine emissions of exempt compounds.
- 503.6 <u>Vapor Pressure:</u> Vapor pressures may be obtained from standard reference texts or may be determined by ASTM D2879-97, "Standard Test Method for Vapor Pressure-Temperature Relationship and Initial Decomposition Temperature of Liquids by Isoteniscope".

- 503.7 <u>Volatile Content of Radiation Curable Materials:</u> Volatile content of radiation curable materials shall be obtained in accordance with ASTM D5403-93, "Standard Test Methods for Volatile Content of Radiation Curable Materials".
- 503.8 <u>Multiple Test Methods:</u> When more than one test method or a set of test methods is specified for any testing, a violation of any requirement of this rule established by any one of the specified test methods or set of test methods shall constitute a violation of this rule.